




CONSTRUCTION	Tufting 5/64" twist pile	PERMANENTLY ANTISTATIC	ISO 6356
STRUCTURE	Tufté 5/64" frisé	ANTISTATIC PERMANENT	≤ 2 kV
STRUKTUR	Getuftet 5/64" Frisé	PERMANENT ANTISTATISCH	
STRUCTUUR	Getuft 5/64" frisé	PERMANENT ANTISTATISCH	
PILE MATERIAL	100% PA 6 IMPREL®	IMPACT NOISE RATING	ISO 140-8
COMPOSITION DU VELOURS		ISOLATION PHONIQUE	26 dB ΔLw
POLMATERIAL		TRITTSCHALLVERBESSERUNG	
POOLMATERIAAL		GELUIDSISOLATIE	
PRIMARY BACKING	Woven PP	SOUND ABSORPTION	ISO 354
SUPPORT	PP tissé	ABSORPTION PHONIQUE	0.20 αw
TRÄGERMATERIAL	PP-Bändchen	SCHALLABSORPTIONSGRAD	
TUFTDOEK	Geweven PP	GELUIDSABSORPTIE	
SECONDARY BACKING	Action Back	THERMAL RESISTANCE	ISO 8302
DOSSIER		RÉSISTANCE THERMIQUE	0.12 m² K/W
RÜCKEN		WÄRMEDURCHLASSWIDERSTAND	
TAPIJTRUG		WARMTEDOORLAATWEERSTAND	
PILE WEIGHT	Ca. 1.200 gr/m²	FASTNESS TO LIGHT	ISO 105-B02
POIDS DU VELOURS		SOLIDITÉ À LA LUMIÈRE	≥ 5-6
POLEINSATZGEWICHT		LICHTECHTHEIT	
POOLGEWICHT		LICHTECHTHEID	
TOTAL WEIGHT	Ca. 2.126 gr/m²	COLOUR FASTNESS TO WATER	EN ISO 105-E01
POIDS TOTAL		SOLIDITÉ À L'EAU	≥ 4-5
GESAMTGEWICHT		WASSERRECHTHEIT	
TOTAAL GEWICHT		WATERECHTHEID	
PILE HEIGHT	Ca. 6,5 mm	FIRE RESISTANCE	EN 13501-1
EPAISSEUR DU VELOURS		COMPOTEMENT AU FEU	Cfl-s1
POLHÖHE		BRENNVERHALTEN	only with full adhesion
POOLHOOGTE		BRANDGEDRAG	
TOTAL HEIGHT	Ca. 8,6 mm	RUBBING FASTNESS	EN ISO 105-X12
EPAISSEUR TOTAL		SOLIDITÉ AU FROTTEMENT	≥ 4
GESAMTHÖHE		REIBECHTHEIT	
TOTALE DIKTE		WRIJFECHTHEID	
TUFT DENSITY	Ca. 274 400/m²	NUMBER OF COLOURS	24
NOMBRES DE POINTS		NOMBRES DE COULEURS	
NOPPENZAHL		ANZAHL FARBEN	
AANTAL PUNTEN		AANTAL KLEUREN	
PILE DENSITY	Ca. 0.159 g/cm³	WIDTH	EN ISO 3018
DENSITÉ DU VELOURS		LARGEUR	ca. 400 cm
POLROHDICHTHEIT		BREITE	
POOLDICHTHEID		BREEDTE	
CLASSIFICATION	EN 1307		
CLASSEMENT	33 - LC5		
KLASSIFIKATION			
CLASSIFICATIE			
CASTOR CHAIR SUITABILITY	EN 985		
CHAISE À ROULETTES	A: intensive use		
STUHLROLLENEIGNUNG			
ROLSTOELGESCHIKTHEID			
STAIR SUITABILITY	EN 1963		
ESCALIERS	A: intensive use		
TREPPENEIGNUNG			
TRAPPENGESCHIKTHEID			



durana ^{AB}



▲ 36



▲ 35



▲ 34



▲ 43



▲ 90




▲ 39




▲ 78



▲ 74



▲ 95



▲ 93



▲ 49



▲ 47



▲ 72



▲ 53



▲ 54



▲ 96



▲ 97



▲ 48




▲ 27



▲ 23



▲ 10



▲ 17



▲ 98



▲ 91